



TYNKOLIT-U 340

Areas of application:	Limits and levels absorbency, reinforces the groundwork, facilitates painting and increases paint adhesion to the groundwork.
Product features:	Increases groundwork adhesion Universal Regulates groundwork absorbency Waterproof Frost-proof
Material base:	<ul style="list-style-type: none"> • Polymer dispersion • Quartz aggregate • Titanium white • Refining agents • Water
Application:	
Conditions for application:	Apply in temperatures from +5°C to +25°C, these temperature refer to air, groundwork and product temperature. All groundwork surfaces must be load-bearing, tight, stable, even and clean and, if required, primed with GRUNTOLIT-W 301 Groundwork must be cleared from dust, grease, anti-adhesive solutions, paint residue, mold, algae, moss, etc., free from cracks and saline efflorescence.
Surface:	Eradicate all expressions of biological aggression on the groundwork using the SEPTOBUD 1008 solution. Repair all cracked and scratched surfaces with the 428 leveling grout or other, suitable for the groundwork type. The grout in the repaired sites must be completely dry and fixed. Cover all surfaces not intended for priming before the primer is applied.
Types of substrate:	Reinforcing layer in the thermal insulation system: without additional priming Cement-lime plaster: With high absorbency, prime with GRUNTOLIT-W 301 Plasterboard: without additional priming Concrete: without additional priming Cement plaster: without additional priming
Preparation:	Ready-to-use product. Do not dilute with water or mix with other materials. Mix thoroughly before use.
Application:	Primer; apply with a roller, brush or using spray application The average drying time is 24 hours. Protect against frostbite, precipitation, excessively high temperatures and strong wind during application and drying.
Notes:	When conducting works in adverse weather conditions, use special covers limiting the effects of external factors. Slight room ventilation is admitted.
Storage:	Maximally 12 months In dry areas and in non-damaged factory packaging, at temperatures from +5°C to +25°C.
Product compliant with:	Technical Approval ETA-07/0192
Amount per unit Unit per pallet	<ul style="list-style-type: none"> • 20 kg/bucket, 33 Stk./Pal. • 7 kg, 80 EH/Kiste

TYNKOLIT-U 340



Technical data

Consumption	from 0.2 to 0.3kg/m ²
pH	c.a. 7
Color	white or dyed
Drying time	c.a. 2-4h
The possibility of performing further works	c.a. 24 hours in optimal conditions

General notes:

This sheet supersedes all previous versions. The information included in this technical sheet represents the current knowledge and practical experience. The information sheet contains general information only and shall not be construed as any basis for manufacturer liability for performance and use. Differences and specific execution conditions may occur. The product is to be used according to the required level of technical knowledge and OHS principles. Avoid skin contact and protect the eyes. In the case of eye contact, wash the eyes abundantly with clean water and seek medical assistance. The use of gloves, goggles and protective clothing is recommended.